




PLCLS is coextruded cast polypropylene film, both sides heat sealable with very wide heat sealing range on the non-treated side for high speed packaging, one side corona treated. The film is suitable for packing of food products and goods with general use.

TYPICAL APPLICATIONS

- General purpose packaging
- High speed packaging HFFS and VFFS
- High quality rotogravure and flexo printing



Properties	Test Methods	Deviation	Typical Values							
			20	25	30	35	40	50	60	70
Thickness μm			20	25	30	35	40	50	60	70
Average thickness deviation, %		\pm	2.5	2.5	2.5	2.0	2.0	2.0	2.0	2.0
Density, g/cm^3			0.9							
Unit weight, g/m^2		$\pm 5\%$	18.0	22.5	27	31.5	36	45	54	62
Yield, m^2/kg		$\pm 5\%$	55.6	44.4	37	31.8	27.8	22.2	18.5	15.9
Coefficient of Friction*	ASTM D 1894		0.12 ÷ 0.25							
Elongation at break, %										
MD	ASTM D 882	± 100	650	650	650	650	650	650	650	650
TD			650	650	650	650	650	650	650	650
Sealing range** nontr/nontr		-	90÷130	90÷130	90÷130	90÷130	90÷130	90÷130	90÷130	90÷130
Tensile strength, MPa										
MD	ASTM D 882	± 15	50	50	50	50	50	50	50	50
TD			25	25	25	25	25	25	25	25
Surface treatment, dynes/cm	ASTM D 2578a	-	Min 36	Min 36	Min 36	Min 36	Min 36	Min 36	Min 36	Min 36

*- Dynamic COF nontreated/nontreated side

** - the sealing range starts with SIT (sealing initiation temperature), film-film, nontreated side

The specified values are based on average results, measured by the manufacturer during standard production. They should not be considered as Data Sheet of any particular product.

The end user should be satisfied as to the suitability of the product for the intended application and the present regulatory regime. Therefore, Plastchim-T AD disclaims any liability for damages arising from the non-suitability of the product for the effected application.

Ability for printing/ lamination is guaranteed for the period of 3 months from the manufacturing date indicated on the label attached to every roll.

Other parameters listed above are guaranteed for the period of 6 months from the manufacturing date.



FOOD CONTACT

The CPP Film complies with all national and international standards and requirements for food contact. The Declaration of Compliance is accessible at www.plastchim-t.com

PACKING

	Core Diameter	Outer Diameter *	Notes
Vertical	152 mm (6`) 76 mm (3`)	≤ 550 mm	≤ 700 mm – two or more rows > 700 mm – one row
Horizontal	152 mm (6`) 76 mm (3`)	≤ 770 mm	

(*) In case of no other requirements

TOLERANCES

Weight tolerance, depending on the order volume	Width tolerance	Length tolerance
≤ 1 000 kg ± 20% 1001 ÷ 10 000 ± 10% >10 000 ± 5%	± 2 mm	±5 %

Storage and Transportation Terms & Conditions

Palletizing of goods is done according to customer's requirements.

The storage of all goods is in dry, covered and clean warehouses.

The transportation of the goods is carried out in dry, covered and clean means of transport.

The recommended temperature of storage/transportation is 10-30°C. If the temperature is not within the recommended limits, the following issues may occur:

- Decrease of dyne level
- Higher haze of the film
- Poor adhesion of the film surface that on a later stage could be an issue for laminating and printing
- Extremely low COF that can trouble further processing

Excessive humidity can be a reason for film blocking.

It is recommended that CPP film should be tempered at operating room temperature above 20°C for minimum 24 hours before use. In case of transporting and storing the films below 5°C seasoning time should be extended to a minimum of 48 hours.

Before printing or laminating of CPP films it is recommended the use of an inline treatment station in order to boost the treatment level of the printable surface or to be used adequate primer to achieve a perfect product.

Claims regarding to the transportation are accepted within 1 week after the delivery date. If any, a record has to be taken in the CMR.